

CYNPOL LL0218H

Linear Low Density Polyethylene Resin

Product Description

CYNPOL LL0218H is a butene linear low density polyethylene for film extrusion. This product is designed for excellent draw down and puncture strength. It contains 1,500ppm slip & 6,300ppm anti-block for blown film applications.

Applications

Automatic packaging film, general purpose blown film, trash bags.

Requirement meets

CYNPOL LL0218H meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520 which is covering safe use of polyolefin articles intended for food contact.

Physical Properties

Property ¹	Test Method	Unit	Typical Value	Reference
Melt Index	ASTM D-1238	g/10min	2.0	2.16kg at 190 °C
Density	ASTM D-792	g/cc	0.918	
Tensile Strength, Break	ASTM D-882	MPa	MD 30 TD 23	
Elongation	ASTM D-882	%	MD 600 TD 650	
Secant Modulus1%	ASTM D-882	MPa	MD 150 TD 170	
Elmendorf Tear	ASTM D-1922	g	MD 95 TD 300	
Dart Drop Impact Strength, F50	ASTM D-1709	g	95	

¹The technical information on properties is based on film 25µm thickness and all data information herein refers to typical values. Since conditions of product use is outside our control, we make no warranties and assume no liability in connection with any use of this information.



For technical support & more information

Vinmar International Ltd

16825 Northchase Drive, Suite 1400, Houston, Texas 77060 USA T +1.281.618.1300 F +1.281.618.1398 www.vinmar.com

We make no other representation or warranties, express or implied, including, without limitation, warranties of merchantability and fitness for a particular purpose, and expressly disclaims all other representations and warranties and any and all other obligations or liabilities on the part of us. No person is authorized to give any other warranties or to assume any other liability on behalf of us unless made or assumed in writing by us.

Revised September 2017